

Received on 17 April 2016; received in revised form, 11 May 2016; accepted, 19 June 2016; published 31 August 2016

## A STUDY TO ASSES THE ANTIBACTERIAL PROPERTY OF FIVE ENDODONTIC SEALERS

Meenakshi Mohan\* and N. P. Muralidharan

Department of Microbiology, Saveetha Dental College, Chennai - 600077, Tamil Nadu, India

**ABSTRACT: Aim:** The study aims to analyze the antibacterial property of various endodontic sealers against *Streptococcus mutans* and *Enterococcus faecilis*. **Objective:** Pulpal tissues are frequently infected by bacteria and are considered to be the commonest etiological agents of pulpal necrosis and periapical lesions, which needs endodontic treatment for its cure. Microorganisms play an important role in endodontic failures, which is commonly due to incomplete elimination of bacteria from the canal or due to the recolonization of bacteria by leakages. Thus it becomes important for the sealers to have antibacterial property. To make long-lasting restorations, the materials should be made antibacterial. The objective of this study is to check for the antibacterial property of the restorative sealers. **Methodology:** The antimicrobial activity of five endodontic sealers (zinc oxide eugenol, amalgam, light cure composite, calcium hydroxide, and glass ionomer) was assessed against *Enterococcus faecilis* and *Streptococcus mutans* using the agar diffusion method. **Reason:** Microorganisms being the commonest reason for endodontic treatment failure, endodontic sealers should possess an antimicrobial property.

**Keywords:** Endodontic failures, Antibacterial property, Endodontic sealers, Agar diffusion method

### Correspondence to Author:

Meenakshi Mohan


BDS, Saveetha Dental College, Chennai - 600077, Tamil Nadu, India.

**E-mail:** drmeena.mohan23@gmail.com

**INTRODUCTION:** Secondary caries is the major factor that influences the longevity of dental restorations<sup>1-4</sup>. Microorganisms may also be present beneath a restoration as a result of microleakage or incomplete removal of caries during tooth preparation<sup>5</sup>. Secondary caries is found to be the main reason for the restoration failure of dental restoratives, including resin composites and glass-ionomer cement<sup>6, 7, 8, 9</sup>. To make long-lasting restorations, the materials should be antimicrobial<sup>10</sup>.

This can be achieved by instrumentation, irrigation, and intra-canal medication. Endodontic sealers are also known to have inherent antibacterial activity, which may help to control the population of microorganisms<sup>11</sup>. Although, bacteria superficially adhering to root canal dentin might be more easily killed than those protected in the depths of dentinal tubules, bacteria inside the dentinal tubules might also be affected by antibacterial components leaching from the irrigation solution, intracanal medication, and endodontic filling and sealing materials<sup>12</sup>.

The ultimate goal of root canal therapy might be considered to be the complete elimination of all microorganisms from the root canal system. Unfortunately, this appears to be impossible in typical clinical situations<sup>13</sup>. However, the use of endodontic sealers with antibacterial properties

	<p><b>DOI:</b> 10.13040/IJPSR.0975-8232.IJLSR.2(8).130-32</p>
	<p>The article can be accessed online on <a href="http://www.ijlsr.com">www.ijlsr.com</a></p>
<p>DOI link: <a href="http://dx.doi.org/10.13040/IJPSR.0975-8232.IJLSR.2(8).130-32">http://dx.doi.org/10.13040/IJPSR.0975-8232.IJLSR.2(8).130-32</a></p>	

may help in reducing the number of infecting microorganisms and in eradicating infection<sup>14</sup>. Antimicrobial properties are desirable in endodontic sealers as the sealer is likely to come in direct contact with any microorganisms remaining in the dentinal tubules and undebrided parts of the root canal system<sup>15</sup>.

The success of endodontic treatment depends on eliminating the microorganisms from the root canal and also by preventing them from re-entering the canal system. Microorganisms play an important role in endodontic failures, which is commonly due to incomplete elimination of bacteria from the canal or due to the recolonization of bacteria by leakages. Cleansing and obturation of the root canal eliminates any pre-existing infection and provide a "hermetic seal" that is desired to prevent the bacteria from penetrating the apical tissue. The cavity is then restored using sealers to prevent leakage. The high success rate of endodontically treated teeth despite the presence of bacterial leakage along the obturated root canal emphasizes the importance of coronal seal.


A study found that only 8.6% of the failures were caused by endodontic causes, 59.4% of failures were a restorative failure, and 32% of failures were periodontal. This study aims to evaluate the antimicrobial property of three major restorative sealers - the light-cured composite, glass ionomer cement, amalgam.

**MATERIALS AND METHOD:** The study analyzed the antibacterial activity of five major endodontic sealers against *Streptococcus mutans* and *Enterococcus faecilis* by agar diffusion method. The five endodontic sealers used in this study were zinc oxide eugenol, Glass ionomer cement, light cure composite, amalgam and calcium hydroxide.

Five pure cultures of *Enterococcus faecilis* and *Streptococcus mutans* were made in a Nutrient agar in which five wells each was made. The endodontic sealers were mixed according to its manufacturer's guidelines and was inoculated into the wells of both *Enterococcus faecilis* and *Streptococcus mutans*. The plates were incubated at 37 °C for 24 h after which the zone of inhibition was measured in millimeter, and a standard mean value of each was calculated.

**TABLE 1: OBSERVATION**

Endodontic sealer	Zone of inhibition in <i>Enterococcus faecilis</i> (in mm)	Zone of inhibition in <i>Streptococcus mutans</i> (in mm)
Zinc oxide eugenol	19.8	30
Composite	0	0
Glass ionomer cement	20	12.5
Calcium hydroxide	18.3	26.8
Amalgam	22	27



**FIG. 1: COMPARING THE EFFICACY OF ENDODONTIC SEALERS AGAINST STREPTOCOCCUS MUTANS AND ENTEROCOCCUS (zone size measured in mm)**

**RESULT:** The study shows that all the endodontic sealers used in this study except light cure composite have an effective antibacterial activity against both the organisms. The mean diameters of zones of inhibition of 5 endodontic sealers are tabulated above. However, zinc oxide eugenol and amalgam showed the highest antibacterial activity against *Streptococcus mutans* and *enterococcus*, respectively, whereas comparatively, light cure composite shows no antibacterial activity.

**DISCUSSION:** Microbes are considered to be the primary causative agents in endodontic diseases. Especially, the anaerobic gets well adapted to survive in the necrotic pulp chamber and in the dentinal tubules in which the blood supply and oxygen supply is limited.<sup>16</sup> *E. faecalis* and *S. mutans*, are common isolates from infected root canals, which has been used in numerous studies of antibacterial properties. Hence, *E. faecalis* and *S. mutans* were preferred in this study. The antibacterial properties of the five endodontic sealers were evaluated by using agar diffusion method<sup>17, 18</sup>. Agar diffusion method is one of the most often and commonly used method to assess the antibacterial activity of dental materials<sup>19, 20</sup>. The agar diffusion assay is a method for quantifying the ability of antibiotics to inhibit

bacterial growth. Interpretation from this assay relies on model-dependent analysis, which is based on the assumption that antibiotics diffuse freely in the solid nutrient medium<sup>21</sup>. But then, several limitations of this method include, lack of standardization of inoculum density, inadequate culture medium, agar viscosity, size and number of specimens per plate, plate-storage condition, and time and temperature of incubation<sup>22</sup>. Several root canal sealers are currently available, which are based on various formulas. An ideal root canal sealer should be inert, dimensionally stable, and possess good antimicrobial activity with low toxicity toward the surrounding tissue<sup>23</sup>.

In this study, amalgam, glass ionomer cement, light cure composite, zinc oxide eugenol, calcium hydroxide were used to study the antibacterial property. Different results were obtained from the ADT of different root-canal sealers. More assaying methods can be used in the process of evaluating antibacterial properties of dental materials to compare the results in further studies.

**ACKNOWLEDGEMENT:** Nil

**CONFLICT OF INTEREST:** Nil

## REFERENCES:

- Mjor IA and Toffenetti F : Placement and replacement of amalgam restorations in Italy. *Oper Dent* 1992; 17: 70-73.
- Mjor IA : The reasons for replacement and the age of failed restorations in general dental practice. *Acta Odontol Scand* 1997; 55: 58-63.
- Mjor IA and Qvist V : Marginal failures of amalgam and composite resin restorations: 8-year findings. *J Dent* 1998; 26: 311-17.
- Mjor IA, Shen C, Eliasson ST and Richter S: Placement and replacement of restorations in dental practice in Iceland. *Oper Dent* 2002; 27: 117-23.
- De Schepper EJ, Thrasher MR and Thurmond BA: Antibacterial effects of light-cured liners. *Am J Dent* 1989; 2: 74-76.
- Barkhordar RA, Kempler D, Pelzner RRB and Stark MM: Antimicrobial action of glass-ionomer lining cement on *S. sanguis* and *S. mutans*. *Dent Mater* 1989; 5: 281-82.
- H. Forss and Widstrom E: Reasons for Restorative Therapy and Longevity of Restorations in Adults. *Acta Odontologica Scandinavica* 2004; 62(2): 82-86.
- Manhart J, Garcia-Godoy F and Hickel R: Direct Posterior Restorations: Clinical Results and New Developments. *Dental Clinics of North America* 2002; 46(2): 303-39.
- Deligeorgi V, Mjor IA and Wilson NH: An Overview of Reasons for the Placement and Replacement of Restorations. *Primary Dental Care* 2001; 8(1): 5-11.
- Craig RG and Power JM: *Restorative Dental Materials*. 11<sup>th</sup> Edition, Mosby-Year Book Inc., St Louis 2002.
- Zhang H, Shen Y, Dorin Ruse N and Haapasalo M: Antibacterial activity of endodontic sealers by Modified Direct Contact Test against *Enterococcus faecalis*. *Journal of Endodontics* 2009; 35: 1051-5.
- Kayaoglu G, Erten H, Alaçam T and Ørstavik D: Short-term antibacterial activity of root canal sealers towards *Enterococcus faecalis*. *Int Endod J* 2005; 38: 483-88.
- Sundqvist G, Figdor D, Persson S and Sjogren U: Microbiologic analysis of teeth with failed endodontic treatment and the outcome of conservative re-treatment. *Oral Surgery, Oral Medicine, Oral Pathology, Oral Radiology, and Endodontics* 1998; 85: 86-93.
- Grossman L: Antimicrobial effect of root canal cement. *Journal of Endodontics* 1980; 6: 594-7.
- Nair PN, Henry S, Cano V and Vera J: Microbial status of the apical root canal system of human mandibular first molars with primary apical periodontitis after "one-visit" endodontic treatment. *Oral Surgery, Oral Medicine, Oral Pathology, Oral Radiology and Endodontics* 2005; 99: 231-52.
- Lai CC, Huang FM and Yang HW: Antimicrobial activity of four root canal sealers against endodontic pathogens. *Clin Oral Investig* 2001; 5: 236-9.
- Chong BS, Owadally ID, Pitt Ford TR and Wilson RF: Antibacterial activity of potential retrograde root filling materials. *Endod Dent Traumatol* 1994; 10: 66-70.
- Fuss Z, Weiss EI and Shalhav M: Antibacterial activity of calcium hydroxide-containing endodontic sealers on *Enterococcus faecalis in-vitro*. *Int Endod J* 1997; 30: 397-02.
- Al-Khatib ZZ, Baum RH, Morse DR, Yesilsoy C, Bhambhani S and Furst ML: The antimicrobial effect of various endodontic sealers. *Oral Surg Oral Med Oral Pathol* 1990; 70: 784-90.
- Weiss E, Shalhav M and Fuss Z: Assessment of antibacterial activity of endodontic sealers by a direct contact test. *Endod Dent Traumatol* 1996; 12: 179-84.
- Bonev B, Hooper J and Parisot J: Principles of assessing bacterial susceptibility to antibiotics using the agar diffusion method. *Journal of Antimicrobial Chemotherapy* 61(6): 1295-1301.
- Pumarola J, Berastegui E, Brau E, Canalda C and Jimenez de Anta MT: Antimicrobial activity of seven root canal sealers. Results of agar diffusion and agar dilution tests *Oral Surg Oral Med Oral Pathol* 1992; 74: 216-20.
- Slutzky-Goldberg I, Slutzky H, Solomonov M, moshonov J, Weiss E and Matalon S: Antibacterial properties of four endodontic sealers. *Journal of endodontics*. Doi: 10.1016/j.joen.2008.03.012

### How to cite this article:

Mohan M and Muralidharan NP: A study to assess the antibacterial property of five endodontic sealers. *Int J Life Sci & Rev* 2016; 2(8): 130-32. doi: 10.13040/IJPSR.0975-8232.IJLSR.2(8).130-32.